




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G01N 21/03, B29C 51/00		A1	(11) International Publication Number: WO 99/18422
			(43) International Publication Date: 15 April 1999 (15.04.99)
(21) International Application Number: PCT/SE98/01776		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).	
(22) International Filing Date: 2 October 1998 (02.10.98)		Published <i>With international search report.</i>	
(30) Priority Data: 9703624-8 3 October 1997 (03.10.97) SE			
(71) Applicant (for all designated States except US): HEMOCUE AB [SE/SE]; P.O. Box 1204, S-262 23 Ängelholm (SE).			
(72) Inventors; and (75) Inventors/Applicants (for US only): JANSSON, Lars [SE/SE]; Råggatan 2, S-262 53 Ängelholm (SE). OLSSON, Per [SE/SE]; Svedjegatan 11, S-260 80 Munka Ljungby (SE). POGORZELSKI, Norbert [SE/SE]; Gustavslundsvägen 274, S-252 60 Helsingborg (SE). HULTGREN, Ingrid [SE/SE]; Vaddögatan 20, S-257 30 Helsingborg (SE).			
(74) Agent: AWAPATENT AB; P.O. Box 5117, S-200 71 Malmö (SE).			

(54) Title: PRODUCTION OF MICROCUVETTES

Composure of Film Cuvettes in Lab Scale

(57) Abstract

The invention concerns a method for continuous production of disposable capillary plastic microcuvettes including the steps of providing a first and a second sheet; providing at least one depression having a predetermined depth at a predetermined place in at least one of the sheets; introducing at least one additive or reagent in at least one depression; joining the first sheet and the second sheet for obtaining a body member including at least one cavity, the inner walls of which are defined by the at least one depression and a predetermined area of the opposite sheet and cutting out microcuvettes including at least one cavity and having a predetermined size and configuration from the body member, in such a way that at least one cavity of the microcuvette is communicating with the exterior atmosphere of the microcuvette through a capillary sample inlet opening. The invention also concerns a cuvette prepared according to the new method.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

PRODUCTION OF MICROCUVETTES

The present invention concerns a new method for producing disposable microcuvettes or microdevices.

A microcuvette for sampling a fluid, mixing the sample with a reagent and directly making optical analyses of the sample mixed with the reagent is previously known from US patent 4,088,448. This cuvette comprises a body member including two planar surfaces defining an optical path and placed at a predetermined distance from one another to determine the optical path length and to define a cavity having an inlet communicating said cavity with the exterior of the body member.

The cavity has a predetermined fixed volume, and the predetermined distance is chosen so as to permit the sample to enter the cavity by capillary force. Furthermore, a reagent is applied on the cavity surface.

This known cuvette has several advantages when compared with the conventionally used devices. It permits sampling of a liquid, mixing and chemically reacting it with a suitable reagent for e.g. colour development in the same vessel as the one used for the subsequent measurement. The cuvette disclosed in US patent 4,088,448 thus simplifies the sampling procedure, reduces the number of utensils and, depending on the type of analysis, considerably improves the exactitude of the analysis by making the analysing procedure independent of the operating technique of the operator making the analysis.

At present microcuvettes based on the microcuvette disclosed in US patent 4 088 488 and US patent 5 674 457 are marketed for analysing e.g. hemoglobin and glucose. The accuracy and precision in the currently used cuvette production is excellent. An obvious disadvantage is that each cuvette has to be moulded in one piece and a

CONFIRMATION COPY

specific tool is required for every type of cavity. Another disadvantage is the comparatively short stability due to the decomposition of the reagent mixture in e.g. the glucose cuvettes. The instability originates from the fact that different components of the reagents cannot be physically separated during the storage as, during the manufacture, the reagents are incorporated into the cuvette as a solution, which is subsequently dried. The dried reagent layer formed in the cuvette cavity therefore includes an intimate mixture of different reagent components. Furthermore, the design, particularly the depths of cuvettes having more than one cavity, cannot be selected at will and in view of the specific requirements for the specific analytical determination, but is restricted by the manufacturing method. For instance it is not possible to produce a cuvette having two cavities with different depths, of which the deepest cavity is most remote from the inlet opening by the current cuvette manufacturing technique.

In view of these problems with the presently used cuvettes and the manufacturing thereof a new manufacturing method, which satisfies the following conditions, is desired. The new manufacturing method should fulfil the following requirements:

It should make it possible to separate reagents, which would give the cuvette a prolonged stability.

It should be possible to effectively control the reagent distribution and separation of reagent components on the surface of the cavity.

It should permit a high flexibility in the choice of the cavity design.

It should permit the production of microcuvettes for photometric analysis with both high accuracy and precision.

It should permit the production of microcuvettes, wherein a deeper cavity is provided more remote from the sample inlet opening than a more shallow, capillary inlet cavity. The deeper cavity could be capillary or non-capillary. When capillary, the deeper cavity is less capillary than the capillary inlet cavity.

It should permit continuous, high capacity production.

It should permit a modular production system, where the modules could be replaced or easily modified for a particular application.

It has now been found that these conditions can be satisfied by using the new manufacturing method according to the present invention.

In brief, this manufacturing method concerns the production of disposable capillary microcuvettes or microdevices, comprising the steps of

- providing a first and a second sheet;
- providing at least one depression having a predetermined depth at a predetermined place in at least one of the sheets;
- introducing at least one additive and/or reagent into at least one depression;
- placing the sheets in a superimposed relationship;
- joining the first sheet and the second sheet for obtaining a body member including at least one capillary cavity having a predetermined volume, the inner walls of the cavity being defined by the at least one depression and a predetermined area of the opposite sheet, the distance between these inner walls defining a predetermined optical path length,
- cutting out microcuvettes including at least one cavity and having a predetermined size and configuration from the body member, in such a way that at least one cavity of the microcuvette is communicating with the exterior atmosphere of the microcuvette through a

capillary sample inlet opening. The inlet opening is preferably formed by this cutting.

According to this method, a new disposable capillary plastic microcuvette or microdevice for
5 sampling a liquid, mixing the sample with reagents and directly making analyses of the sample mixed with the reagents is obtained. This microcuvette comprises a capillary sample inlet opening and at least one cavity including at least one dry reagent and/or additive. The
10 cavity communicates with the exterior atmosphere of the microcuvette through the capillary inlet opening, through which the sample, e.g. whole blood, is drawn by capillary action. Furthermore, the new microcuvette is distinctive in that it is made up by two joined sheets,
15 in at least one of which is provided at least one depression at a predetermined place and having a predetermined depth. The place and orientation of the depressions are not critical. Preferably the depressions are provided in such a way that each depression is surrounded by the sheet material. The alternative in which
20 the depression is provided at the edge of the sheet is however also within the scope of the invention. In this alternative the capillary inlet opening is formed by the edge of the joined sheets.

25 A most important feature of the invention is based on the discovery that a very accurate predetermined depth suitable for very precise optical measurements can be produced using the vacuum forming or stamping technique, the vacuum forming technique being preferred
30 as in this case a positive die is used and the surface facing the capillary cavity is not affected by the die. An additional advantage with a positive die is that it is independent of the thickness of the film material, which allows cavity formation with a very high
35 precision.

The inner walls of the cavity are formed by the depression and a predetermined area of the inner surface of the adjoining sheet.

5 Optionally, holes are provided in at least one sheet. These holes are arranged in such a way that they form a vent hole in the final microcuvette.

10 Preferably the cavity has a predetermined volume. The inner surfaces of the walls defining the cavity are preferably essentially plane-parallel and define an optical path length or volume according to Beer's law.

15 The cavity includes a least one dried reagent and/or additive. If the reagent is made up by more than one substance, the different substances may be separated from each other in the same cavity by using e.g. a printing technique, such as ink jet printing or screen printing. The reagent, which is chosen depending on the analysis to be performed, is preferably introduced in the form of a solution which is subsequently dried e.g. by hot air.

20 The sheets, at least one of which is provided in the form of a continuous film, are preferably made of one and the same polymer material which should be thermoplastic and transparent. It is also preferred that the polymer is self-supporting. Examples of suitable
25 polymer materials are PVC, PET, polystyrenes and polycarbonates.

30 The depressions are preferably obtained by vacuum forming or stamping. It is also preferred that a plurality of depressions be provided in one of the sheets and that the other sheet be planar. In this case each cavity is formed by a planar cover or lid and the depression.

35 Before joining the sheets, a reagent and/or additive, such as a surface modifying agent, may be provided in one or more depressions.

The surfaces of the sheets to be matched are then provided with an UV-sensitive adhesive, such as Loctite 3106 for PVC and Loctite 3108 for polycarbonate materials, which does not require a solvent that may damage the polymer material and which cures when irradiated with UV-light. Preferably the adhesive is applied by screen printing. When the surfaces have been pressed together the adhesive is cured by radiation, such as UV radiation. Other methods of joining the sheets, such as ultrasound welding, have turned out to be less attractive due to problems of obtaining accurate and reproducible cavity depths, i.e. optical paths. According to an embodiment of the invention the inner surfaces of the sheets, i.e. the surfaces facing the cavities, are provided with embossments determining the depth of the capillary cavity and guiding optional superfluous adhesive to areas between the embossments in such a way the adhesive does not have any impact on the cavity depth. Since in the production of microcuvettes, the cavity depth is very small, at most 1 mm, and a predetermined accurate value of this depth is critical for the subsequent use of the cuvette, the provision of embossments is preferred. Advantageously these embossments are arranged in a predetermined pattern.

When a very precise cavity depth of the cuvette is required it is important that the depression(s) and the joining of the sheets are performed in such a way that the cavity depth is independent of subsequent steps in the cuvette production method. According to the invention it is preferable that the depression(s) is (are) performed by vacuum forming technique using a positive die. It is also preferable that the inner surface of the sheets are provided with embossments prior to the adhesion of the sheets. The embossment is used to guide optional superfluous adhesive to areas between the embossment. It is also preferable to use an

adhesive, which does not modify the surface of the sheet, such as an adhesive, cured by UV-light.

The microcuvette or microdevice according to the invention is especially useful for making optical analyses on fluids such as whole blood, serum, plasma, urine, spinal and interstitial fluids. After the sampling procedure when e.g. blood is sucked from the finger tip of a patient into the microcuvette by capillary action, the microcuvette is inserted into a separate spectrophotometer calibrated for the desired type of analysis. The use of a separate spectrophotometer is a major difference between the present invention and the invention disclosed in EP 172 450, the object of which is to provide an analysis instrument in which the reaction chamber, which is also called a cuvette, is produced within the analysis instrument. This arrangement is perceived to provide an economic advantage in that it eliminates the cost of the prior formation of the chamber. When the reaction chamber or cuvette leaves the instrument, the reaction as well as the analysis are completed and the cuvette is disposed of. The EP patent thus concerns cuvettes which can only be used in connection with the analysis instrument, in which the cuvette is formed, and not for analysis in different other analysis instruments. Furthermore, the principle for the production of cavities in these known cuvettes is based on the deformation of a plastic material into close contact with a mould cavity by using a jet of hot air which is quite contrary to the principle according to the present invention which uses vacuum forming in order to obtain the cavity. Another important difference is the type of inlet opening for reagents and samples as well as the methods of introducing the samples and reagents.

The invention is further illustrated by but not limited to the example disclosed in Fig. 1.

A first sheet or lid sheet and a second sheet or base sheet of PVC are provided separately. Eight venting holes are provided in the lid sheet and a reagent, e.g. an enzyme is ink printed next to the holes. Eight
5 cavities are vacuum-formed simultaneously in the base sheet. The depths of the cavities were selected to be 140 μm but other cavity depths may be used. The sheets were dried in tunnels and joined together by using UV sensitive glue (Loctite 3106). Cuvettes were
10 subsequently cut from the multiple cuvette sheet, by cutting or punching and packed.

CLAIMS

1. A method for production of disposable capillary plastic microcuvettes comprising the steps of
- providing a first and a second sheet
 - 5 - providing at least one depression having a predetermined depth at a predetermined place in at least one of the sheets;
 - introducing at least one additive and/or reagent into at least one depression;
 - 10 - placing the sheets in a superimposed relationship;
 - joining the first sheet and the second sheet for obtaining a body member including at least one capillary cavity having a predetermined volume, the inner walls of the cavity being defined by the at least one depression
 - 15 and a predetermined area of the opposite sheet, the distance between these inner walls defining a predetermined optical path length'
 - cutting out microcuvettes including at least one cavity and having a predetermined size and configuration
 - 20 from the body member, in such a way that at least one cavity of the microcuvette is communicating with the exterior atmosphere of the microcuvette through a capillary sample inlet opening, which is preferably formed by this cutting.
- 25 2. The method according to claim 1 for continuous production, wherein at least one sheet is provided in the form of a continuous plastic film.
3. The method according to claim 1 or 2, wherein the at least one depression is provided by vacuum
- 30 forming.
4. The method according to any one of claims 1-3, wherein a plurality of depressions are arranged in at least one sheet.

5. The method according to any one of claims 1-4, wherein embossments are provided in a predetermined pattern around the depressions.

6. The method according to any one of claims 1-5, wherein venting holes are provided in one sheet.

7. The method according to any one of claims 1-6, comprising providing an UV sensitive adhesive on those surfaces of the sheets which are to be joined.

8. The method according to claim 7, wherein the adhesive is applied by screen printing.

9. The method according to any one of claims 1-8, wherein the additive and/or reagent is liquid and provided by printing.

10. The method according to any one of claims 1-9, wherein the additive and/or reagent is dried before the sheets are placed in a superimposed relationship.

11. The method according to any one of claims 1-10, wherein the predetermined distance between the walls of the capillary cavity defining the optical path is less than 1 mm.

12. A disposable plastic microcuvette comprising a capillary sample inlet opening, a capillary cavity having a predetermined volume and including at least one dry chemical additive and/or reagent and communicating with the exterior atmosphere of the microcuvette through the inlet opening, which microcuvette is made up by at least two sheets joined by an adhesive, in at least one of which is provided at least one vacuum-formed depression having a predetermined depth, the inner walls of the cavity being formed by the depression and a predetermined area of the inner surface of the adjoining sheet.

13. The microcuvette according to claim 12 for making optical analysis, wherein the walls consist of an essentially transparent material.

14. The microcuvette according to any one of claims 12-13, wherein embossments are arranged for providing an accurate and precise optical path length.

5 15 The microcuvette according to any one of claims 12-14, wherein one sheet is essentially planar.

16. The microcuvette according to any one of claims 12-15, wherein the cavity includes a fluid-modifying agent which is essentially inert in analysis.

10 17. The microcuvette according to any one of claims 12-16, including cavities having different depths.

18. The microcuvette according to any one of claims 12-17, wherein, depending on the water solubility, the reagents in the cavity are provided on the predetermined area and/or in the depression(s).

15 19. A disposable plastic microcuvette prepared according to any one of claims 1-11, comprising a capillary sample inlet opening, a capillary cavity including at least one dry chemical additive and/or reagent and communicating with the exterior atmosphere
20 of the microcuvette through the inlet opening, which microcuvette is made up by at least two joined sheets, in at least one of which is provided at least one depression having a predetermined depth, the inner walls of the cavity being formed by the depression and a pre-
25 determined area of the inner surface of the adjoining sheet

1/1

Composure of Film Cuvettes in Lab Scale




Figure 1

INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 98/01776

A. CLASSIFICATION OF SUBJECT MATTER

IPC6: G01N 21/03, B29C 51/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: B29C, G01N, B01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4088448 A (JAN EVERT LILJA ET AL), 9 May 1978 (09.05.78), column 2, line 47 - line 52 --	1-19
A	EP 0172540 A2 (E.I. DU PONT DE NEMOURS AND COMPANY), 26 February 1986 (26.02.86), figure 1 --	1-19
A	US 4792373 A (PAUL K. HSEI ET AL), 20 December 1988 (20.12.88), column 6, line 56 - line 59, figure 11 --	1-19
A	US 3698822 A (MICHAEL L. POLANYI), 17 October 1972 (17.10.72) -----	1-19

☐ Further documents are listed in the continuation of Box C.
 ☒ See patent family annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

17 December 1998

Name and mailing address of the ISA/

Swedish Patent Office

Box 5055, S-102 42 STOCKHOLM

Facsimile No. +46 8 666 02 86

Date of mailing of the international search report

25 -01- 1999

Authorized officer

Maria Börlin

Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

01/12/98

International application No.
PCT/SE 98/01776

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4088448 A	09/05/78	AT 376300 B	25/10/84
		AT 683876 A	15/03/84
		AU 497567 B	14/12/78
		AU 1822976 A	06/04/78
		BE 846403 A	17/01/77
		BR 7606475 A	28/06/77
		CA 1057078 A	26/06/79
		CH 612505 A	31/07/79
		DE 2641097 A,C	07/04/77
		DK 150804 B,C	22/06/87
		DK 435376 A	30/03/77
		FI 59672 B,C	29/05/81
		FI 762737 A	30/03/77
		FR 2325920 A,B	22/04/77
		GB 1557984 A	19/12/79
		HK 18083 A	03/06/83
		IE 43188 B	31/12/80
		IN 145819 A	30/12/78
		JP 1125827 C	30/11/82
		JP 52055679 A	07/05/77
		JP 57011414 B	04/03/82
		JP 57066343 A	22/04/82
		LU 75854 A	04/05/77
		NL 181381 B,C	02/03/87
		NL 7610712 A	31/03/77
		SE 399768 B,C	27/02/78
		SE 7510863 A	30/03/77
EP 0172540 A2	26/02/86	SE 0172540 T3	
		CA 1261719 A	26/09/89
		DK 378485 A	22/02/86
		GR 852005 A	19/12/85
		JP 1707270 C	27/10/92
		JP 3075070 B	28/11/91
		JP 61057858 A	24/03/86
US 4792373 A	20/12/88	US 4863693 A	05/09/89
		CA 1273466 A	04/09/90
		EP 0229153 A,B	22/07/87
		JP 6037082 B	18/05/94
		JP 62503088 T	10/12/87
US 3698822 A	17/10/72	WO 8607565 A	31/12/86
		DE 2007405 A	08/10/70
		FR 2035058 A	18/12/70